

# Krusty Koin Number #

# 09

**Obverse**



**Reverse**



**Base Measurements**

Type of Metal:	<u>Unknown</u>
Diameter (mm):	<u>18</u>
Thickness (mm):	<u>2</u>
Weight (gm):	<u>2.38</u>
Coating Color:	<u>Brown</u>
AE Size:	<u>AE3</u>
<b>Additional Notes / Information</b>	

**Method used for this experiment**



Method Used: Soaking, Scrubbing, Repeat  
 Product Used: WD40  
 Product URL: [www.wd40.com](http://www.wd40.com)

**Notes on Method:**

Not mixed with anything

**Product Information:**

**NEED PRODUCT INFO**

**Initial Mixture - Specific's about everything**

**Container Used**



4 oz Glad Ware Mini Rounds

**Description of the mixture.**

100% WD40 for the initial soak. Sprayed into the Glad container. Be careful when spraying so that you don't get WD40 all over.

**Parts Cleaning Solution:** 20 (ml)

**Solution %** 100.0%

**Parts Distilled Water:** 0 (ml)

**Experiment Data - WD40**


Start Date of Experiment: 9/6/2003 (mm/dd/yyyy)  
 Time Started: 19:00 Military Time  
 End Date of Experiment: (mm/dd/yyyy)  
 Time Ended: Military Time

**Duration of Experiment**  
 Duration in Days: 0  
 Duration in Hours: 0.00

Interval **Interval 1 - 14 Day(s) 2 Hour(s) from last point of measurement** 1

Interval Date: 9/20/2003 Interval Duration (days) 14  
 Interval Time: 21:00 Interval Duration (hours) 338.00  
 Total Experiment Duration: 14 Days 2.00 Hour(s)

**Notes on Duration/delays etc.**



**Base Measurements**  
 Type of Metal: Unknown  
 Diameter (mm): 18  
 Thickness (mm): 2  
 Weight (gm): 2.32  
 Coating Color: Brown  
 AE Size: AE3



**Solution for Next Interval**  
 Parts Cleaning Solution (ml): 25  
 Parts Other (ml): 0  
 Solution Strength %: 100.0%

**Notes / Observations / Tools Used / Etc..**  
 100% solution of WD40. It was a long soak, not because I meant to.. But because I got to busy to check on it... I do not recommend that you let anything soak this long in a new solution. Scrubbed and brushed. Seemed to make a decent first impression. We'll see what this solution has to bring.

Interval **Interval 2 - 5 Day(s) 9 Hour(s) from last point of measurement** 2

Interval Date: 9/26/2003 Interval Duration (days) 5  
 Interval Time: 6:00 Interval Duration (hours) 129.00  
 Total Experiment Duration: 19 Days 11.00 Hour(s)

**Notes on Duration/delays etc.**



**Base Measurements**  
 Type of Metal: Unknown  
 Diameter (mm): Not Measured  
 Thickness (mm): Not Measured  
 Weight (gm): 1.96  
 Coating Color: Brown  
 AE Size: AE3

**Solution for Next Interval**  
 Parts Cleaning Solution (ml): 30  
 Parts Other Distilled Wtr (ml): 30  
 Solution Strength %: 50.0%

**Notes / Observations / Tools Used / Etc..**  
 We'll part of the coin broke off, and it almost looked like it may have been a silvered coin... the coins seems pitted... I think I can make out some features... but not sure that they will clean up at all. Not sure that this coin is going to make it. And I am wondering if I am to blame with that ultra long first soak :- ( .. going to a 50% solution to slow damage down if possible.

**Experiment Data - WD40**



Start Date of Experiment: 9/6/2003 (mm/dd/yyyy)  
 Time Started: 19:00 Military Time  
 End Date of Experiment: (mm/dd/yyyy)  
 Time Ended: Military Time

**Duration of Experiment**  
 Duration in Days: 0  
 Duration in Hours: 0.00

Interval Interval 3 - 9 Day(s) 18 Hour(s) from last point of measurement 3

Interval Date: 10/5/2003 Interval Duration (days) 9  
 Interval Time: 15:00 Interval Duration (hours) 225.00  
 Total Experiment Duration: 28 Days 20.00 Hour(s)

**Notes on Duration/delays etc.**




**Base Measurements**  
 Type of Metal: Unknown  
 Diameter (mm): 17  
 Thickness (mm): 2  
 Weight (gm): 1.96  
 Coating Color: Brown  
 AE Size: AE3

**Solution for Next Interval**  
 Parts Cleaning Solution (ml): 30  
 Parts Other Distilled Wtr (ml): 0  
 Solution Strength %: 100.0%

**Notes / Observations / Tools Used / Etc..**



Went to 100% solution to see if the outer layer is really crust or coin.  
 have high hopes for this coin. It pretty much appears to be  
 foaming on WD40 see pic ->



Interval Interval 4 - 0 Day(s) 0 Hour(s) from last point of measurement 4

Interval Date: Interval Duration (days) 0  
 Interval Time: Interval Duration (hours) 0.00  
 Total Experiment Duration: 0 Days 0.00 Hour(s)

**Notes on Duration/delays etc.**



**Base Measurements**  
 Type of Metal: Unknown  
 Diameter (mm):  
 Thickness (mm):  
 Weight (gm):  
 Coating Color:  
 AE Size: Unknown

**Solution for Next Interval**  
 Parts Cleaning Solution (ml): 0  
 Parts Other \_\_\_\_\_ (ml): 0  
 Solution Strength %: 100.0%

**Notes / Observations / Tools Used / Etc..**